

(19)



JAPANESE PATENT OFFICE



PATENT ABSTRACTS OF JAPAN

(11) Publication number: **2004063010 A**(43) Date of publication of application: **26.02.04**

(51) Int. Cl.

G11B 5/735(21) Application number: **2002220802**(22) Date of filing: **30.07.02**(71) Applicant: **TDK CORP**(72) Inventor: **IDE TSUTOMU
YAMAZAKI KATSUHIKO**

(54) MAGNETIC RECORDING MEDIUM

(57) Abstract:

PROBLEM TO BE SOLVED: To suppress abrasive ability of a back coat layer to a low level when improving durability by incorporating alumina in the back coat layer.

SOLUTION: In this magnetic recording medium, a back coat layer includes at least carbon black and alumina as non-magnetic powder, and an alumina content (x) pts. wt. and abrasive ability (y) of the back coat layer are within a range surrounded by four equations: $y=4.6x+12.2$, $y=4.1x+10.8$, $y=13$, and $y=17$, when a graph is drawn on xy orthogonal coordinate axes, wherein, (y) indicates width length in the running direction of a surface formed by wear of a Sendust(R) bar when the corner part of the Sendust bar 2 of a square pillar type are supported by a tension of 0.526 N/cm per unit width in a state in which they are pushed perpendicularly into the back coat layer to an entering angle 12°, and the bar 2 runs one reciprocation of 50m at a running speed of 0.3 m/s.

COPYRIGHT: (C)2004,JPO

